

Attorney Docket No. 740756-2681

Application No. 10/728,987

Page 2

BEST AVAILABLE COPY**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Canceled)
2. (Currently Amended) A method for forming a film comprising the steps of:
 - introducing a reactive gas into a reaction chamber;
 - applying a pulsed electromagnetic wave to said reactive gas to convert said reactive gas into a plasma;
 - applying a continuous electromagnetic wave to said reactive gas so that said continuous electromagnetic wave is superposed on said pulsed electromagnetic wave; and
 - forming the film on a surface of an object in said reaction chamber,wherein a power value of said pulsed electromagnetic wave is higher than a power value of said continuous electromagnetic wave, and
wherein said film comprises a material selected from the group consisting of carbon, diamond like carbon, i-carbon, metal, and insulating ceramics.
3. (Previously Presented) A method according to claim 2 further comprising a step of applying a magnetic field for performing an electron cyclotron resonance in said reaction chamber.
4. (Currently Amended) A method for forming a film comprising the steps of:
 - introducing a reactive gas into a reaction chamber;
 - applying a pulsed microwave to said reactive gas to convert said reactive gas into a plasma;
 - applying a continuous electromagnetic wave to said reactive gas so that said

W717403.1

continuous electromagnetic wave is superposed on said pulsed microwave; and
forming the film on a surface of an object in the reaction chamber using the
plasma,
wherein a power value of said pulsed microwave is higher than a power value
of said continuous electromagnetic wave, and
wherein said film comprises a material selected from the group consisting of
carbon, diamond like carbon, i-carbon, metal, and insulating ceramics.

5. (Previously Presented) A method according to claim 4 further
comprising a step of applying a magnetic field for performing an electron cyclotron
resonance in said reaction chamber.

6. (Currently Amended) A method for forming a film comprising the
steps of:
introducing a reactive gas into a reaction chamber;
applying a pulsed electromagnetic wave to said reactive gas to convert said
reactive gas into a plasma;
applying a continuous electromagnetic wave to said reactive gas so that said
continuous electromagnetic wave is superposed on said pulsed electromagnetic wave; and
forming the film on a surface of an object in said reaction chamber,
wherein a power value of said pulsed electromagnetic wave is higher than a
power value of said continuous electromagnetic wave, and
wherein a frequency of said pulsed electromagnetic wave is the same as a
frequency of said continuous electromagnetic wave, and
wherein said film comprises a material selected from the group consisting of
carbon, diamond like carbon, i-carbon, metal, and insulating ceramics.

7. (Previously Presented) A method according to claim 6 further
comprising a step of applying a magnetic field for performing an electron cyclotron
resonance in said reaction chamber.

Attorney Docket No. 740756-2681
Application No. 10/728,987
Page 4

8. (Currently Amended) A method for forming a film comprising the steps of:

- introducing a reactive gas into a reaction chamber;
- applying a pulsed electromagnetic wave to said reactive gas to convert said reactive gas into a plasma;
- applying a continuous electromagnetic wave to said reactive gas so that said continuous electromagnetic wave is superposed on said pulsed electromagnetic wave; and
- forming the film on a surface of an object in said reaction chamber,

wherein a power value of said pulsed electromagnetic wave is higher than a power value of said continuous electromagnetic wave, and

wherein a frequency of said pulsed electromagnetic wave is different from a frequency of said continuous electromagnetic wave, and

wherein said film comprises a material selected from the group consisting of carbon, diamond like carbon, i-carbon, metal, and insulating ceramics.

9. (Previously Presented) A method according to claim 8 further comprising a step of applying a magnetic field for performing an electron cyclotron resonance in said reaction chamber.

10. (Previously presented) A method for forming a metallic film comprising the steps of:

- introducing a reactive gas into a reaction chamber;
- applying a pulsed electromagnetic wave to said reactive gas to convert said reactive gas into a plasma;
- applying a continuous electromagnetic wave to said reactive gas so that said continuous electromagnetic wave is superposed on said pulsed electromagnetic wave; and
- forming the metallic film on a surface of an object in said reaction chamber,

and

wherein a power value of said pulsed electromagnetic wave is higher than a power value of said continuous electromagnetic wave.

Attorney Docket No. 740756-2681
Application No. 10/728,987
Page 5

11. (Previously Presented) A method according to claim 10 wherein said metallic film comprises a material selected from the group consisting of tungsten, titanium, molybdenum and a silicide thereof.

12. (Previously Presented) A method according to claim 10 further comprising a step of applying a magnetic field for performing an electron cyclotron resonance in said reaction chamber.

13. (Previously presented) A method for forming a metallic film comprising the steps of:

introducing a reactive gas into a reaction chamber;

applying a pulsed microwave to said reactive gas to convert said reactive gas into a plasma;

applying a continuous electromagnetic wave to said reactive gas so that said continuous electromagnetic wave is superposed on said pulsed microwave; and

forming the metallic film on a surface of an object in the reaction chamber using the plasma,

wherein a power value of said pulsed microwave is higher than a power value of said continuous electromagnetic wave.

14. (Canceled)

15. (Previously Presented) A method according to claim 13 further comprising a step of applying a magnetic field for performing an electron cyclotron resonance in said reaction chamber.

16. (Previously presented) A method for forming a metallic film comprising the steps of:

introducing a reactive gas into a reaction chamber;

applying a pulsed electromagnetic wave to said reactive gas to convert said reactive gas into a plasma;

Attorney Docket No. 740756-2681
Application No. 10/728,987
Page 6

applying a continuous electromagnetic wave to said reactive gas so that said continuous electromagnetic wave is superposed on said pulsed electromagnetic wave; and
forming the metallic film on a surface of an object in said reaction chamber,
wherein a power value of said pulsed electromagnetic wave is higher than a power value of said continuous electromagnetic wave, and
wherein a frequency of said pulsed electromagnetic wave is the same as a frequency of said continuous electromagnetic wave.

17. (Previously Presented) A method according to claim 16 further comprising a step of applying a magnetic field for performing an electron cyclotron resonance in said reaction chamber.

18. (Previously presented) A method for forming a metallic film comprising the steps of:

introducing a reactive gas into a reaction chamber;
applying a pulsed electromagnetic wave to said reactive gas to convert said reactive gas into a plasma;
applying a continuous electromagnetic wave to said reactive gas so that said continuous electromagnetic wave is superposed on said pulsed electromagnetic wave; and
forming the metallic film on a surface of an object in said reaction chamber,
wherein a power value of said pulsed electromagnetic wave is higher than a power value of said continuous electromagnetic wave, and
wherein a frequency of said pulsed electromagnetic wave is different from a frequency of said continuous electromagnetic wave.

19. (Canceled)

20. (Previously Presented) A method according to claim 18 further comprising a step of applying a magnetic field for performing an electron cyclotron resonance in said reaction chamber.

Attorney Docket No. 740756-2681
Application No. 10/728,987
Page 7

21. (Canceled)

22. (Canceled)

23. (Canceled)

24. (Canceled)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.